



The ISF® Process Reduces Dynamic Corrosion Fatigue

Problem

Corrosion resistance is of prime importance for the materials used in the aerospace industry, which often operate in corrosive environments. It is well known that material subjected to cyclic load far below the ultimate tensile stress can fail, a process called fatigue. If the metal is simultaneously exposed to a corrosive environment, the failure can take place



REM Surface Engineering
325 W Queen Street
Southington, CT 06489 USA
Phone: (860) 621-6755
Fax: (860) 621-8822
Email: sales@remchem.com

REM Surface Engineering
2107 Longwood Drive
Brenham, TX 77833 USA
Phone: (979) 277-9703
Fax: (979) 277-0309
Email: sales@remchem.com

Solution

ISF® processed parts have an increased cycle life when subjected to dynamic corrosion fatigue of martensitic stainless steel by

- Reducing the surface area
- Eliminating surface tensile stresses
- Enriching the chromium oxide content of the surface

Test

Martensitic Stainless steel specimens, which the ISF® processed to an R2 <2.5 µm. where compared to reference specimens, which were hand polished in the longitudinal to an R2 of 4.0 µm. The Specimens were tested to a runout of 5 x 10⁷ cycles by reverse bending

Medium	Stress (MPa)	Stress (MPa)	Stress Percent Increase from ISF® Process
	Hand Polished	ISF® Processed	
Air	250 ± 385	250 ± 445	16
Water	250 ± 250	250 ± 370	48
22% NaCl, 80° C pH 7 (sea water 3.5% NaCl)	250 ± 250	250 ± 195	117

REM Surface Engineering
8912 Mississippi Street
Merrillville, IN 46410 USA
Phone: (860) 736-1477
Email: sales@remchem.com

REM Surface Engineering, GmbH.
Siemensring 68d
D-47877 Willich, DE
Phone: +49 2154 82070-0
Email: sales-eu@remchem.com

www.remchem.com

REM QMS is certified to ISO 9001:2015 and AS9100:2016 Rev D

ISF® and REM logo are registered trademarks of REM Surface Engineering. All rights reserved.